

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 11342569

PUBLICATION DATE : 14-12-99

APPLICATION DATE : 22-04-98

APPLICATION NUMBER : 10112535

APPLICANT : MITSUI CHEM INC;

INVENTOR : TERASHI YUICHIRO;

INT.CL. : B32B 27/32 B32B 1/02 B32B 27/28 C08L 23/04 //(C08L 23/04 , C08L 23:26 , C08L 29:04)

TITLE : POLYETHYLENIC MULTILAYERED LAMINATE, CONTAINER AND RESIN COMPOSITION

ABSTRACT : PROBLEM TO BE SOLVED: To obtain a polyethylenic multilayered laminate and a container excellent in characteristics such as impact resistance, rigidity, gasoline barrier properties, interlaminar adhesion or the like and capable of being utilized as recyclable scraps.

SOLUTION: A multilayered laminate includes a base layer (A1) containing a polyethylene resin (a1) with MFR of 0.001-0.5 g/10 min and a density of 0.940-0.980 g/cm³ and an adhesive layer (A2) containing a modified ethylene/ α -olefin copolymer (a2) with a density of 0.900-0.940 g/cm³ graft-modified with an unsaturated carboxylic acid or a derivative thereof, a barrier layer (B) containing an ethylene/vinyl alcohol copolymer (b) and a compsn. layer (C) containing a polyethylenic resin compsn. (c) containing 80-99.5 wt.% of an ethylenic polymer (a) and 0.5-20 wt.% of an ethylene/vinyl alcohol copolymer (b) and having Izod impact strength (-40°C, the presence of notches) of 100 J/m or more and a container is obtained from this laminate.

COPYRIGHT: (C)1999,JPO